



Equinox HG has 4 added advantages to help you shine—7% higher gloss readings, 20% less drying time, less odor and improved resistance to black heel marks. It's Equinox, but better.

DIRECTIONS


Read all directions and Safety Data Sheets (SDS) before using.

1. For a floor that has been stripped, properly neutralized, rinsed and allowed to dry thoroughly, apply 5-6 thin coats using a clean synthetic mop. Allow the floor to dry thoroughly between coats and prior to burnishing.
2. Optional: Apply 2 thin coats of floor sealer for old or porous floors or for high traffic areas, then apply 4 coats of finish.
3. For a floor that has been deep scrubbed and allowed to dry thoroughly, apply 1-2 thin coats using a clean synthetic mop. Allow floor to dry thoroughly between coats and prior to burnishing.

PRODUCT INFO

Product Code	139FS	139MPE	139PL5	139DR
Volume	2.50 US gallons	4 liters	5 US gallons	55 US gallons
Shipping Package	2 x 2.5 gallons	4 x 4 liters	per unit	per unit
Pallet Quantity	48	48	36	4

SURFACES



TECHNICAL DATA

Description	Polymer emulsion
Appearance	Milky white
Specular Gloss (60°) ASTM D1455-87 (2008)	> 85
Viscosity (Brookfield) @ 68°F (20°C)	<10 centipoise
Coverage Rate	2500 to 3000 ft ² /gal 61 to 74 m ² /liter
Dry Time	About 25 minutes
Buffability	Excellent
Removability ASTM D1792-06	Excellent
VOC 40 CFR Part 59 Subpart C	0.06%
Non-Volatile Solids ASTM D2834-95 (2008)	22%
Fragrance	Slight ammoniacal
Slip Resistance ULTM410	Meets requirements
Shelf Life ASTM D1791-93 (2008)	1 year
Density ASTM D1475-98 (2008)	8.5 lb/gal @ 68°F 1.02 kg/L @ 20°C
Detergent Resistance ASTM D3207-92 (2008)	Excellent
Freeze/Thaw ASTM D3209-93 (2008)	Passes 3 cycles
Container	2.5 US gal/9.5 L (FS packaging) 1.06 US gal/4 L (MPE packaging) 5 US gal/19 L (PL5 packaging) 55 US gal/208 L (DR packaging)



Floor Coating and Finishing materials
as to slip resistance only. 42E6