

# Total Eclipse™

## ULTRA HIGH SPEED FLOOR COATING

Urethane-fortified UHS finish that provides superior impact and scratch resistance.



No Intentionally  
Added PFAS

SURFACES



### WHY TOTAL ECLIPSE:

## IMPACT RESISTANT, PREVENTS CHIPPING & SCRATCHING

Urethane-fortified

## REPAIRABLE, HIGHLY BURNISHABLE

Acrylic co-polymer

### TECHNICAL DATA

Description	Acrylic co-polymer emulsion
Appearance	Milky white
Specular Gloss (60°) ASTM D1455-87 (2008)	>85
Viscosity (Brookfield) (@ 68°F (20°C))	<10 centipoise
Coverage Rate	2500 to 3000 ft <sup>2</sup> /gal 61 to 74 m <sup>2</sup> /liter
Dry Time	About 30 minutes
Buffability	Excellent
Removability ASTM D1792-06	Excellent
VOC 40 CFR Part 59 Subpart C	0.44%
Total Solids	27%
Non-Volatile Solids ASTM D2834-95 (2008)	22%
Fragrance	Slight ammoniated
Slip Resistance ULTM410	Meets requirements
Shelf Life ASTM D1791-93 (2008)	1 year
Density ASTM D1475-98 (2008)	8.5 lb/gal @ 68°F 1.02 kg/L @ 20°C
Detergent Resistance ASTM D3207-92 (2008)	Excellent
Freeze/Thaw ASTM D3209-93 (2008)	Passes 3 cycles

#### DISINFECTANT COMPATIBILITY:

The following Pioneer Eclipse disinfectants are safe to use on this floor coating when correctly diluted and used according to the product directions. Bleach and other corrosives may cause damage.

MeridiClean All Purpose Cleaner & Disinfectant

NeutraQuat 256 Germicidal Disinfectant

Triton XLC Bathroom Cleaner & Disinfectant

### DIRECTIONS

Apply thin coats using a clean synthetic mop. Allow floor to dry thoroughly between coats and prior to burnishing.

Read all directions and Safety Data Sheet (SDS) before using.

Directions and SDS are available for download at [pioneereclipse.com](http://pioneereclipse.com)



Floor Coating and Finishing materials as to slip resistance only. 42E6

Product Code	138FS
Volume	2.50 US gallons
Shipping Package	2 x 2.5 gallons
Pallet Quantity	48